

Strength and **Durability** for **LiFe**[®]



FEATURES

**Linings and Gaskets
for Ductile Iron Pipe**

Last Revised:
November 2022

Description	Maximum Service Temperature (°F) ^{1, 2} Uses ³			
	Water & Sewer Push-On & Mechanical Joint Gaskets	Air ^{4, 5} Push-On Joint Gaskets	Mechanical Joint Gaskets	
SBR (Styrene Butadiene)	150°	150°	125°	Common: Drinking Water, Sea Water, Sanitary Sewage, Reclaimed Water, Raw Water, Storm Water
EPDM (Ethylene Propylene Diene Monomer)	212°	200°	150°	Common: Alcohols, Dilute Acids, Dilute Alkalis, Ketones (MEK, Acetone), Vegetable Oil. Other Acceptable Services: Drinking Water, Sea Water, Sanitary Sewage, Reclaimed Water, Raw Water, Storm Water
Nitrile (NBR) (Acrylonitrile Butadiene)	150°	150°	125°	Common: Hydrocarbons, Fats, Oils, Greases, Chemicals, Oils & Fluids, Refined Petroleum. Other Acceptable Services: Drinking Water, Sanitary Sewage, Reclaimed Water, Raw Water, Storm Water
Neoprene® (CR) (Polychloroprene)	200°	180°	150°	Common: Greasy Waste. Other Acceptable Services: Sea Water, Sanitary Sewage, Reclaimed Water, Raw Water, Storm Water
Viton®; Fluorel® (FKM) ⁶ (Fluorocarbon)	212°	300°	300°	Common: Aromatic Hydrocarbons and Fuels, Acids, Vegetable Oils, Petroleum Products, Chlorinated Hydrocarbons, Most Chemicals and Solvents. Other Acceptable Services: Drinking Water, Reclaimed Water, Raw Water, Storm Water

¹Maximum service temperatures listed are intended as general guidelines for Ductile iron pipe gaskets. For service temperatures greater than those listed, consult pipe manufacturer for specific recommendations.

²Maximum service temperature is not usually a meaningful parameter for piping gaskets; however, low temperatures during pipeline installation may necessitate precautions. Consult pipe manufacturer for pertinent recommendations.

³Water, including sewage, with low levels of the listed contaminants.

⁴Lubricating oil in the air will adversely affect SBR and EPDM performance.

⁵SBR, Nitrile, or Neoprene are not recommended for air exposure in wastewater treatment systems.

⁶Consult pipe manufacturer for availability of FKM push-on gaskets.

Description	Maximum Service Temperature (°F) ⁷	Uses	Thicknesses
Portland Cement Mortar ⁸ with Sealcoat without Sealcoat	150° 212°	Common: Drinking Water Sea Water Non-Septic Gravity Sewers Sanitary Sewer Force Mains Reclaimed Water	Standard or Double (ANSI/AWWA C104/A21.4)
Fusion-Bonded Epoxy (Fittings Only)	120° - 150° ⁷	Common: Drinking Water Non-Septic Gravity Sewers Sanitary Sewer Force Mains Reclaimed Water	(ANSI/AWWA C116/A21.16) ¹⁰
Petroleum Asphalt Coating	150°	Common: Air	1 mil (nominal)
Ceramic Quartz Filled Amine Cured Novalac Epoxy ⁹	120° - 150° ⁷	Common: Septic Sewers Acids Alkali Waste Pickling Brine Other Acceptable Services: Reclaimed Water	40 mil (nominal)

⁷ Maximum service temperatures listed are intended as general guidelines which may vary depending on service conditions and lining formulation. Consult pipe manufacturer for specific recommendations.

⁸ ASTM C150 Type V sulfate resisting cement is recommended for seawater applications and some reclaimed water applications. Consult pipe manufacturer for specific reclaimed water recommendations.

⁹ Other linings may be available for particular conditions. Consult pipe manufacturer for specific service use and material details.

¹⁰ Recommended lining thicknesses may vary depending on service conditions, epoxy formulation, diameter, and other variables. Consult fitting manufacturer for specific recommendations.

For more information contact DIPRA or any of its member companies.

Ductile Iron Pipe Research Association

An association of quality producers dedicated to the highest pipe standards through a program of continuing research and service to water and wastewater professionals.

P.O. Box 190306
Birmingham, AL 35219
205.402.8700 Tel
www.dipra.org

Member Companies

AMERICAN Ductile Iron Pipe
P.O. Box 2727
Birmingham, Alabama 35202-2727
www.american-usa.com

Canada Pipe Company, Ltd.
55 Frid St. Unit #1
Hamilton, Ontario L8P 4M3 Canada
www.canadapipe.com

McWane Ductile
P.O. Box 6001
Coshocton, Ohio 43812-6001
www.mcwaneductile.com

U.S. Pipe
Two Chase Corporate Drive
Suite 200
Birmingham, Alabama 35244
www.uspipe.com

Social Media

Get in the flow with Ductile iron pipe by connecting with us on [Facebook](#), [Twitter](#), and [LinkedIn](#).

Visit our website, www.dipra.org and click on the YouTube icon for informational videos on Ductile iron pipe's ease of use, economic benefits, strength and durability, advantages over PVC, and more.

